Bulk and Surface Acoustic Waves in Piezoelectric Media Introductory Course on Multiphysics Modelling

Tomasz G. Zieliński

bluebox.ippt.pan.pl/~tzielins/

Institute of Fundamental Technological Research of the Polish Academy of Sciences Warsaw • Poland



2 Piezoelectricity

- The piezoelectric phenomena
- Piezoelectric equations
- Voigt-Kelvin notation

2 Piezoelectricity

- The piezoelectric phenomena
- Piezoelectric equations
- Voigt-Kelvin notation

3 Anisotropic media

- Crystalline materials
- Constitutive matrices for some classes of anisotropy

2 Piezoelectricity

- The piezoelectric phenomena
- Piezoelectric equations
- Voigt-Kelvin notation

3 Anisotropic media

- Crystalline materials
- Constitutive matrices for some classes of anisotropy

4 Bulk acoustic waves in anisotropic media

- Mathematical description
- Characteristic surfaces

1 Introduction

2 Piezoelectricity

- The piezoelectric phenomena
- Piezoelectric equations
- Voigt-Kelvin notation

3 Anisotropic media

- Crystalline materials
- Constitutive matrices for some classes of anisotropy

4 Bulk acoustic waves in anisotropic media

- Mathematical description
- Characteristic surfaces

5 Surface Acoustic Waves (SAW)

- Types of Surface Acoustic Waves
- Partial waves
- Rayleigh waves
- Lamb waves
- Decoupling of Rayleigh waves in piezoelectric media

1 Introduction

2 Piezoelectricity

- The piezoelectric phenomena
- Piezoelectric equations
- Voigt-Kelvin notation

3 Anisotropic media

- Crystalline materials
- Constitutive matrices for some classes of anisotropy

4 Bulk acoustic waves in anisotropic media

- Mathematical description
- Characteristic surfaces

5 Surface Acoustic Waves (SAW)

- Types of Surface Acoustic Waves
- Partial waves
- Rayleigh waves
- Lamb waves
- Decoupling of Rayleigh waves in piezoelectric media

6 SAW examples

- Piezoelectric Rayleigh wave in lithium niobate
- Lamb waves in a lithium niobate plate

1 Introduction

2 Piezoelectricity

- The piezoelectric phenomena
- Piezoelectric equations
- Voigt-Kelvin notation

3 Anisotropic media

- Crystalline materials
- Constitutive matrices for some classes of anisotropy

4 Bulk acoustic waves in anisotropic media

- Mathematical description
- Characteristic surfaces

5 Surface Acoustic Waves (SAW)

- Types of Surface Acoustic Waves
- Partial waves
- Rayleigh waves
- Lamb waves
- Decoupling of Rayleigh waves in piezoelectric media

6 SAW examples

- Piezoelectric Rayleigh wave in lithium niobate
- Lamb waves in a lithium niobate plate

Anisotropic media

Bulk acoustic waves

Surface Acoustic Waves (SAW)

SAW examples

Introduction

- Surface Acoustic Waves (SAW) are acoustic waves which travel along the surface of an elastic material; typically, their amplitude decays exponentially with depth into the substrate.
- Wave propagation in anisotropic media is much more complex than in isotropic materials.
- Piezoelectric materials are inherently anisotropic.

Anisotropic media

Introduction

- Surface Acoustic Waves (SAW) are acoustic waves which travel along the surface of an elastic material; typically, their amplitude decays exponentially with depth into the substrate.
- Wave propagation in anisotropic media is much more complex than in isotropic materials.
- Piezoelectric materials are inherently anisotropic.

Research milestones – on anisotropic wave propagation and Surface Acoustic Waves:

- plane waves in anisotropic media (CHRISTOFFEL, 1877)
- surface wave in an isotropic elastic half-space (RAYLEIGH, 1885)
- double-surface, planar, isotropic, elastic waveguide (LAMB, 1917)
- Rayleigh wave on an anisotropic half-space with cubic crystal symmetry (STONELEY, 1955)
- "forbidden" directions for surface wave propagation do not exist! (LIM and FARNELL, 1968)
- pseudosurface waves (LIM, FARNELL and ROLLINS, 1968, 1969, 1970)
- Bleustein-Gulyaev surface piezoelectric wave (BLEUSTEIN, 1968; GULYAEV, 1969)
- Lamb waves in elastic, anisotropic (cubic) plates (SOLIE and AULD, 1973)
- (decoupling of) Rayleigh waves in orthorhombic, tetragonal, hexagonal, and cubic crystals (ROYER and DIEULESAINT, 1984)

Introduction

2 Piezoelectricity

- The piezoelectric phenomena
- Piezoelectric equations
- Voigt-Kelvin notation

3 Anisotropic media

- Crystalline materials
- Constitutive matrices for some classes of anisotropy

4 Bulk acoustic waves in anisotropic media

- Mathematical description
- Characteristic surfaces

5 Surface Acoustic Waves (SAW)

- Types of Surface Acoustic Waves
- Partial waves
- Rayleigh waves
- Lamb waves
- Decoupling of Rayleigh waves in piezoelectric media

6 SAW examples

- Piezoelectric Rayleigh wave in lithium niobate
- Lamb waves in a lithium niobate plate

(Direct) piezoelectric effect

Piezoelectricity is the ability of some materials (notably crystals and certain ceramics) to generate an **electric charge** in response to applied **mechanical stress**. If the material is not short-circuited, the applied charge induces a **voltage** across the material.



(Direct) piezoelectric effect

Piezoelectricity is the ability of some materials (notably crystals and certain ceramics) to generate an electric charge in response to applied mechanical stress. If the material is not short-circuited, the applied charge induces a **voltage** across the material.

A simple molecular model (of the direct piezoelectric effect)





Before subjecting the material to some external stress:

- the centres of the negative and positive charges of each molecule coincide,
- the external effects of the charges are reciprocally cancelled,
- as a result, an electrically neutral molecule appears.

(Direct) piezoelectric effect

Piezoelectricity is the ability of some materials (notably crystals and certain ceramics) to generate an **electric charge** in response to applied **mechanical stress**. If the material is not short-circuited, the applied charge induces a **voltage** across the material.

A simple molecular model (of the direct piezoelectric effect)



After exerting some pressure on the material:

- the internal structure is deformed,
- that causes the separation of the positive and negative centres of the molecules,
- as a result, little dipoles are generated.



small dipole

(Direct) piezoelectric effect

Piezoelectricity is the ability of some materials (notably crystals and certain ceramics) to generate an **electric charge** in response to applied **mechanical stress**. If the material is not short-circuited, the applied charge induces a **voltage** across the material.

A simple molecular model (of the direct piezoelectric effect)



Eventually:

- the facing poles inside the material are mutually cancelled,
- a distribution of a linked charge appears in the material's surfaces and the material is polarized,
- the polarization generates an electric field and can be used to transform the mechanical energy of the material's deformation into electrical energy.

(Direct) piezoelectric effect

Piezoelectricity is the ability of some materials (notably crystals and certain ceramics) to generate an **electric charge** in response to applied **mechanical stress**. If the material is not short-circuited, the applied charge induces a **voltage** across the material.



Reversibility

The piezoelectric effect is **reversible**, that is, piezoelectric materials always exhibit both:

- the direct piezoelectric effect the production of electricity when stress is applied,
- the converse piezoelectric effect the production of stress and/or strain when an electric field is applied.
 (For example, lead zirconate titanate crystals will exhibit a maximum shape change of about 0.1% of the original dimension.)

(Direct) piezoelectric effect

Piezoelectricity is the ability of some materials (notably crystals and certain ceramics) to generate an **electric charge** in response to applied **mechanical stress**. If the material is not short-circuited, the applied charge induces a **voltage** across the material.

Elastic behaviour $\xleftarrow{\text{Piezoelectric}}{\text{coupling}} \rightarrow \text{Dielectric behaviour}$

Some historical facts and etymology

- The (direct) piezoelectric phenomenon was discovered in 1880 by the brothers Pierre and Jacques Curie during experiments on quartz.
- The existence of the reverse process was predicted by Lippmann in 1881 and then immediately confirmed by the Curies.
- The word *piezoelectricity* means "*electricity by pressure*" and is derived from the Greek *piezein*, which means to squeeze or press.

Piezoelectric equations

Elastodynamics

Equation of motion:

 $\rho \ddot{\boldsymbol{u}} = \nabla \cdot \boldsymbol{T} + \boldsymbol{f}$

- ρ the mass density of the material
- u the mechanical displacement vector
- T the 2nd-rank Cauchy stress tensor
- f the body force vector

Kinematic relations:

 $\boldsymbol{S} = \frac{1}{2} \Big(\nabla \boldsymbol{u} + (\nabla \boldsymbol{u})^{\mathsf{T}} \Big)$

S – the 2nd-rank strain tensor

Constitutive relations for elasticity :

T = c : S

c - the 4th-rank elasticity tensor

Boundary conditions :

 $T\cdot n=\hat{t}$ or $u=\hat{u}$

- \hat{t} the surface load
- \hat{u} the prescribed displacements

Electrostatics

Gauss' law:

$$\nabla \cdot \boldsymbol{D} = q$$

- D the electric displacement vector
- q the body electric charge

Maxwell's law:

$$E = -\nabla \phi$$

- E- the electric filed vector
- ϕ the electric potential

Constitutive relations for dielectrics :

 $D = \epsilon \cdot E$

 ϵ – the 2nd-rank dielectric tensor

Boundary conditions:

$$\hat{D} \cdot n = \hat{Q}$$
 or $\phi = \hat{\phi}$

- \hat{Q} the surface charge
- $\hat{\phi}$ the prescribed electric potential

Anisotropic media

Bulk acoustic waves

Surface Acoustic Waves (SAW)

SAW examples

Piezoelectric equations

► Elastodynamics and electrostatics combined Sourceless equation of motion and Gauss' law:

 $\rho \ddot{\boldsymbol{u}} = \nabla \cdot \boldsymbol{T}, \qquad \nabla \cdot \boldsymbol{D} = 0$

Kinematic relations and Maxwell's law:

$$S = \frac{1}{2} \Big(\nabla u + (\nabla u)^{\mathsf{T}} \Big), \qquad E = -\nabla \phi$$

Boundary conditions:

- mechanical: $T \cdot n = \hat{t}$ or $u = \hat{u}$ - electrical: $D \cdot n = \hat{Q}$ or $\phi = \hat{\phi}$

Piezoelectric materials are anisotropic! (There is *no* isotropic piezoelectric medium.)

The **piezoelectric** effects are realised by **coupling** terms in the **anisotropic constitutive relations**.

Piezoelectric equations

Elastodynamics and electrostatics combined Sourceless equation of motion and Gauss' law:

 $\rho \ddot{\boldsymbol{u}} = \nabla \cdot \boldsymbol{T}, \qquad \nabla \cdot \boldsymbol{D} = 0$

Kinematic relations and Maxwell's law:

$$\boldsymbol{S} = \frac{1}{2} \Big(\nabla \boldsymbol{u} + (\nabla \boldsymbol{u})^{\mathsf{T}} \Big), \qquad \boldsymbol{E} = -\nabla \phi$$

Boundary conditions : mechanical and electrical

Piezoelectric coupling

Constitutive relations for piezoelectric materials (stress-charge form):

$$T = egin{array}{c} e ext{asticity} & ext{inverse effect} \ T = egin{array}{c} c: S & - e^{ extsf{T}} \cdot E \ \end{array} \ D = egin{array}{c} e: S & ext{direct effect} \ + \epsilon \cdot E \ ext{dielectricity} \end{array}$$

- e the 3rd-rank piezoelectric coupling tensor
- c the 4th-rank elasticity tensor in the absence of electric field (E = 0)
- ϵ the 2nd-rank dielectric tensor in the absence of strains (S = 0)

Piezoelectric equations in matrix notation

Voigt-Kelvin convention for index substitution:

 $11 \rightarrow 1$, $22 \rightarrow 2$, $33 \rightarrow 3$, $23 \rightarrow 4$, $31 \rightarrow 5$, $12 \rightarrow 6$

This notation allows to represent:

the 4th-rank tensor of elasticity $c \rightarrow (6 \times 6)$ matrix cthe 3rd-rank tensor of piezoelectric coupling $e \rightarrow (3 \times 6)$ matrix ethe 2nd-rank tensor of dielectric constants $\epsilon \rightarrow (3 \times 3)$ matrix ethe 2nd-rank tensors of strain *S* and stress $T \rightarrow (6 \times 1)$ vectors:

$$S = \begin{bmatrix} S_{11} & S_{22} & S_{33} & 2S_{23} & 2S_{31} & 2S_{12} \end{bmatrix}^{\mathsf{T}}$$
$$\mathbb{T} = \begin{bmatrix} T_{11} & T_{22} & T_{33} & T_{23} & T_{31} & T_{12} \end{bmatrix}^{\mathsf{T}}$$

Consistently, denote also: $u \equiv u$, $\mathbb{D} \equiv D$, $\mathbb{E} \equiv E$, $n \equiv n$.

Piezoelectric equations in matrix notation

Voigt-Kelvin convention for index substitution:

 $11 \rightarrow 1, \quad 22 \rightarrow 2, \quad 33 \rightarrow 3, \quad 23 \rightarrow 4, \quad 31 \rightarrow 5, \quad 12 \rightarrow 6$

 $\begin{array}{ll} \boldsymbol{c} \to \boldsymbol{\mathbb{c}}_{(6\times 6)} & \boldsymbol{e} \to \boldsymbol{\mathbb{e}}_{(3\times 6)} & \boldsymbol{\epsilon} \to \boldsymbol{\mathbb{c}}_{(3\times 3)} \\ \boldsymbol{S} \to \boldsymbol{\mathbb{S}}_{(6\times 1)} & \boldsymbol{T} \to \boldsymbol{\mathbb{T}}_{(6\times 1)} & \boldsymbol{u}, \boldsymbol{D}, \boldsymbol{E} \to \boldsymbol{\mathbb{U}}_{(3\times 1)}, \boldsymbol{\mathbb{D}}_{(3\times 1)}, \boldsymbol{\mathbb{E}}_{(3\times 1)} \end{array}$

Constitutive relations:

$$\mathbb{T} = \mathbb{c}\mathbb{S} - \mathbb{e}^{\mathsf{T}}\mathbb{E}, \qquad \mathbb{D} = \mathbb{e}\mathbb{S} + \mathbb{c}\mathbb{E}.$$

Kinematic relations and Maxwell's law:

$$\mathbb{S} = \mathbf{\nabla}^{\intercal} \mathbf{u}, \qquad \mathbb{E} = -\nabla \phi.$$

Sourceless field equations:

$$\boldsymbol{\nabla} \mathbb{T} - \boldsymbol{\rho} \ddot{\boldsymbol{u}} = \mathbb{O}, \qquad \nabla^{\mathsf{T}} \mathbb{D} = \mathbf{O}.$$

$$\boldsymbol{\nabla} = \begin{bmatrix} \partial_{x_1} & 0 & 0 & 0 & \partial_{x_3} & \partial_{x_2} \\ 0 & \partial_{x_2} & 0 & \partial_{x_3} & 0 & \partial_{x_1} \\ 0 & 0 & \partial_{x_3} & \partial_{x_2} & \partial_{x_1} & 0 \end{bmatrix}, \qquad \nabla = \begin{bmatrix} \partial_{x_1} \\ \partial_{x_2} \\ \partial_{x_3} \end{bmatrix}, \qquad \mathbb{O} = \begin{bmatrix} 0 \\ 0 \\ 0 \end{bmatrix}.$$

Neumann boundary conditions – e.g., homogeneous:

$$\begin{split} \mathbb{N}\mathbb{T} &= \mathbb{O}, \qquad \mathbb{n}^{\mathsf{T}}\mathbb{D} &= 0, \\ \mathbb{N} &= \begin{bmatrix} n_1 & 0 & 0 & 0 & n_3 & n_2 \\ 0 & n_2 & 0 & n_3 & 0 & n_1 \\ 0 & 0 & n_3 & n_2 & n_1 & 0 \end{bmatrix}, \qquad \mathbb{m} = \begin{bmatrix} n_1 \\ n_2 \\ n_3 \end{bmatrix} \end{split}$$

1 Introduction

2 Piezoelectricity

- The piezoelectric phenomena
- Piezoelectric equations
- Voigt-Kelvin notation

3 Anisotropic media

- Crystalline materials
- Constitutive matrices for some classes of anisotropy

4 Bulk acoustic waves in anisotropic media

- Mathematical description
- Characteristic surfaces

5 Surface Acoustic Waves (SAW)

- Types of Surface Acoustic Waves
- Partial waves
- Rayleigh waves
- Lamb waves
- Decoupling of Rayleigh waves in piezoelectric media

6 SAW examples

- Piezoelectric Rayleigh wave in lithium niobate
- Lamb waves in a lithium niobate plate

Piezoelectricity

Anisotropic media

Crystalline materials

- The crystal can be developed in very different forms, yet the relative orientation of the faces is constant.
- The angles between the various faces of a crystal remain unchanged throughout its growth a law. This is the law of constant angles in crystallography.

The law of constant angles

The normals to the crystal faces, drawn from a fixed point, form a geometrically invariant figure (the relative orientation of the faces is constant, although the crystal can be developed in very different forms).

Crystalline materials

The law of constant angles

The normals to the crystal faces, drawn from a fixed point, form a geometrically invariant figure (the relative orientation of the faces is constant, although the crystal can be developed in very different forms).

- The macroscopic properties of crystals suggest their classification according to the symmetry shown by the normals to the natural faces, known as the **point group**.
- The crystalline medium is characterized by an infinity of geometrical points (the nodes), which are equivalent, that is they have the same environment of other points. The set of these nodes forms a three-dimensional lattice, which expresses the periodicity of the crystal in all directions.
- There are **14 lattices** organized in **7 crystal systems**.
- The atomic structure of crystal is determined by the lattice and the atomic group (a group of atoms) assigned to each node:

$\label{eq:crystal} \textbf{Crystal} = \textbf{Lattice} + \textbf{Atomic group}$

Crystalline materials

7 crystal systems and 14 Bravais lattices



| System | Lattices | | Y |
|----------------------------|------------|---|-------------------|
| 1. Triclinic | Р | $\alpha \neq \beta \neq \gamma \neq 90^{\circ}$ | $a \neq b \neq c$ |
| 2. Monoclinic | P, C | $lpha=\gamma=90^\circ$, $eta eq90^\circ$ | $a \neq b \neq c$ |
| 3. Orthorhombic | P, I, C, F | $lpha=eta=\gamma=90^\circ$ | $a \neq b \neq c$ |
| 4. Trigonal (rhombohedral) | P (or R) | $\alpha = \beta = \gamma \neq 90^{\circ}$ | a = b = c |
| 5. Tetragonal (quadratic) | P, I | $\alpha = \beta = \gamma = 90^{\circ}$ | $a = b \neq c$ |
| 6. Hexagonal | Р | $\alpha = \beta = 90^{\circ}, \gamma = 120^{\circ}$ | $a = b \neq c$ |
| 7. Cubic | P, I, F | $\alpha = \beta = \gamma = 90^{\circ}$ | a = b = c |



Crystalline materials

7 crystal systems and 14 Bravais lattices 1 - 11! - - -



| System | Lattices | | |
|--------------------------------|------------|---|-------------------|
| 1. Triclinic | Р | $\alpha \neq \beta \neq \gamma \neq 90^{\circ}$ | $a \neq b \neq c$ |
| 2. Monoclinic | P, C | $lpha=\gamma=90^\circ, \beta eq 90^\circ$ | $a \neq b \neq c$ |
| Orthorhombic | P, I, C, F | $\alpha=\beta=\gamma=90^\circ$ | $a \neq b \neq c$ |
| 4. Trigonal (rhombohedral) | P (or R) | $\alpha = \beta = \gamma \neq 90^{\circ}$ | a = b = c |
| 5. Tetragonal (quadratic) | P, I | $\alpha = \beta = \gamma = 90^{\circ}$ | $a = b \neq c$ |
| 6. Hexagonal | Р | $\alpha = \beta = 90^{\circ}, \gamma = 120^{\circ}$ | $a = b \neq c$ |
| 7. Cubic | P, I, F | $\alpha=\beta=\gamma=90^\circ$ | a = b = c |

- The crystal symmetry is at most equal to that of the lattice \rightarrow a crystal does not necessarily possesses a centre of symmetry.
- There are 32 point symmetry classes of crystals.

Piezoelectricity Anisot

Anisotropic media

Bulk acoustic waves

Surface Acoustic Waves (SAW)

SAW examples

Example: Lithium niobate (LiNbO₃)

Features:

- trigonal system, class 3m,
- strongly piezoelectric,
- large crystals available (cylinders of diameter 10 cm and length more than 10 cm).

To the right: Positions of the lithium and niobium atoms (double and singe cross-hatched circles, respectively) with respect to the oxygen octahedra



Piezoelectricity Anisot

Anisotropic media

Bulk acoustic waves

Surface Acoustic Waves (SAW)

SAW examples

Example: Lithium niobate (LiNbO₃)

Features:

- trigonal system, class 3m,
- strongly piezoelectric,
- large crystals available (cylinders of diameter 10 cm and length more than 10 cm).

To the right: Positions of the lithium and niobium atoms (double and singe cross-hatched circles, respectively) with respect to the oxygen octahedra



ferroelectric

Piezoelectricity Anisotrop

Anisotropic media

Bulk acoustic waves

Surface Acoustic Waves (SAW)

SAW examples

Example: Lithium niobate (LiNbO₃)



Constitutive matrices (for some classes of anisotropy)



Materials:

Gallium arsenide (GaAs) – class $\overline{4}$ 3m, Bismuth and germanium oxide (Bi₁₂GeO₂₀) – class 23

Constitutive matrices (for some classes of anisotropy)



Materials: Zinc oxide (ZnO), Cadmium sulphide (CdS), Ceramic PZT-4

Constitutive matrices (for some classes of anisotropy)



- · : zero component
- : non-zero component

(symmetry about the main diagonal is not shown)

Materials:

Barium sodium niobate (Ba2NaNb5O15)

Trigonal system – class 3m

Constitutive matrices (for some classes of anisotropy)



- : zero component

 : component c₁₁-c₁₂
 : non-zero component
 : equal components
- opposite components

(symmetry about the main diagonal is not shown)

Materials:

Lithium niobate (LiNbO₃), Lithium tantalate (LiTaO₃)

1 Introduction

2 Piezoelectricity

- The piezoelectric phenomena
- Piezoelectric equations
- Voigt-Kelvin notation

3 Anisotropic media

- Crystalline materials
- Constitutive matrices for some classes of anisotropy

4 Bulk acoustic waves in anisotropic media

- Mathematical description
- Characteristic surfaces

5 Surface Acoustic Waves (SAW)

- Types of Surface Acoustic Waves
- Partial waves
- Rayleigh waves
- Lamb waves
- Decoupling of Rayleigh waves in piezoelectric media

6 SAW examples

- Piezoelectric Rayleigh wave in lithium niobate
- Lamb waves in a lithium niobate plate

Piezoelectricity Anisotropic media

Bulk acoustic waves

Surface Acoustic Waves (SAW)

SAW examples

Bulk acoustic waves in piezoelectric media

The plane wave propagation along the direction *n* in a piezoelectric medium is described by the fields of mechanical displacement and electric potential which change with respect to the location x and time t:

$$u_1 \equiv u(\mathbf{x}, t) = A_u \, \mathcal{E}(\mathbf{x}, t), \quad u_2 \equiv v(\mathbf{x}, t) = A_v \, \mathcal{E}(\mathbf{x}, t), \quad u_3 \equiv w(\mathbf{x}, t) = A_w \, \mathcal{E}(\mathbf{x}, t),$$

and for the electric potential:

$$\phi(\boldsymbol{x},t) = A_{\phi} \, \mathcal{E}(\boldsymbol{x},t),$$

where $A_{\mu}, A_{\nu}, A_{\mu}, A_{\phi}$ are constants independent of x and t, and for the given waveform F:

$$\mathcal{E}(\boldsymbol{x},t) = \mathcal{F}(\boldsymbol{n} \cdot \boldsymbol{x} - Vt),$$

where V is the **phase velocity**. These formulas can be rewritten in the matrix form as follows:

$$\mathbb{u} = \mathbb{A}_{u} \mathcal{F}, \quad \phi = A_{\phi} \mathcal{F}, \quad \text{where} \quad \mathbb{A}_{u} = \begin{bmatrix} A_{u} \\ A_{v} \\ A_{w} \end{bmatrix}$$

is the **wave polarization** vector (direction of the particle displacement).

Piezoelectricity Anisotropic media

Bulk acoustic waves

Surface Acoustic Waves (SAW)

SAW examples

Bulk acoustic waves in piezoelectric media

Using the Kelvin-Voigt notation, the mechanical strain and electric field vectors are expressed as

 $\mathbb{S} = \mathbb{N}^{\mathsf{T}} \mathbb{A}_{\mathsf{H}} \mathcal{F}'. \qquad \mathbb{E} = -\mathbb{n} \mathbb{A}_{\phi} \mathcal{F}'.$

Notice that the polarization of electric field is longitudinal. The constitutive relations for the stress and electric displacement vectors are

 $\mathbb{T} = (\mathbb{c}\mathbb{N}^{\mathsf{T}}\mathbb{A}_{\boldsymbol{\mu}} + \mathbb{e}^{\mathsf{T}}\mathbb{n}A_{\boldsymbol{\phi}})\mathcal{F}', \qquad \mathbb{D} = (\mathbb{e}\mathbb{N}^{\mathsf{T}}\mathbb{A}_{\boldsymbol{\mu}} - \mathbb{e}\mathbb{n}A_{\boldsymbol{\phi}})\mathcal{F}'.$

When all these formulas are used for the field equations: $\nabla \mathbb{T} - \rho \ddot{u} = 0$ and $\nabla^{\mathsf{T}} \mathbb{D} = 0$, the following set of equations describing the plane wave propagation in piezoelectric media is obtained.

Equations for plane wave propagation in piezoelectric media

$$\begin{split} \big(\mathbb{N}\mathbb{c}\mathbb{N}^{\mathsf{T}} - \rho V^2 \mathbb{1} \big) \mathbb{A}_{\boldsymbol{u}} + \mathbb{N}\mathbb{e}^{\mathsf{T}}\mathbb{n}A_{\phi} = \mathbb{0}, \\ \mathbb{n}^{\mathsf{T}}\mathbb{e}\mathbb{N}^{\mathsf{T}}\mathbb{A}_{\boldsymbol{u}} - \mathbb{n}^{\mathsf{T}}\mathbb{e}\mathbb{n}A_{\phi} = \mathbf{0}, \end{split}$$

where 1 is the (3×3) -identity matrix. Or, in the matrix form:

$$\begin{bmatrix} \mathbb{N}\mathbb{C}\mathbb{N}^{\mathsf{T}} - \rho V^{2}\mathbb{1} & \mathbb{N}\mathbb{C}^{\mathsf{T}}\mathbb{n} \\ \mathbb{m}^{\mathsf{T}}\mathbb{C}\mathbb{N}^{\mathsf{T}} & -\mathbb{m}^{\mathsf{T}}\mathbb{C}\mathbb{m} \end{bmatrix} \begin{bmatrix} \mathbb{A}_{u} \\ A_{\phi} \end{bmatrix} = \begin{bmatrix} \mathbb{O} \\ 0 \end{bmatrix}$$

Piezoelectricity Anisotrop

Anisotropic media

Bulk acoustic waves

Surface Acoustic Waves (SAW)

SAW examples

Bulk acoustic waves in piezoelectric media

Equations for plane wave propagation in piezoelectric media

$$\begin{split} \mathbb{N}\mathbb{c}\mathbb{N}^{\mathsf{T}} - \rho V^2 \mathbb{1} \big) \mathbb{A}_{\boldsymbol{u}} + \mathbb{N}\mathbb{e}^{\mathsf{T}}\mathbb{n}A_{\phi} &= \mathbb{0}, \\ \mathbb{n}^{\mathsf{T}}\mathbb{e}\mathbb{N}^{\mathsf{T}}\mathbb{A}_{\boldsymbol{u}} - \mathbb{n}^{\mathsf{T}}\mathbb{e}\mathbb{n}A_{\phi} &= \mathbf{0}, \end{split}$$

where 1 is the (3×3) -identity matrix. Or, in the matrix form:

$$\begin{bmatrix} \mathbb{N}\mathbb{c}\mathbb{N}^{\mathsf{T}} - \rho V^2 \mathbb{1} & \mathbb{N}\mathbb{e}^{\mathsf{T}}\mathbb{n} \\ \mathbb{n}^{\mathsf{T}}\mathbb{e}\mathbb{N}^{\mathsf{T}} & -\mathbb{n}^{\mathsf{T}}\mathbb{e}\mathbb{n} \end{bmatrix} \begin{bmatrix} \mathbb{A}_{u} \\ A_{\phi} \end{bmatrix} = \begin{bmatrix} \mathbb{0} \\ \mathbb{0} \end{bmatrix}$$

The last equation in the set gives the following formula:

$$A_{\phi} = \frac{\mathbf{n}^{\mathsf{T}} \mathbf{e} \mathbf{N}^{\mathsf{T}}}{\mathbf{n}^{\mathsf{T}} \mathbf{e} \mathbf{n}} \mathbb{A}_{\mathbf{u}}$$

Christoffel matrix equation

$$\begin{bmatrix} \mathbb{G} - \rho V^2 \mathbb{1} \end{bmatrix} \mathbb{A}_{u} = \mathbb{O}, \quad \text{where} \quad \mathbb{G} = \mathbb{N} \mathbb{c} \mathbb{N}^{\mathsf{T}} + \frac{\mathbb{N} \mathbb{c}^{\mathsf{T}} \mathbb{n} \mathbb{n}^{\mathsf{T}} \mathbb{c} \mathbb{N}^{\mathsf{T}}}{\mathbb{n}^{\mathsf{T}} \mathbb{c} \mathbb{n}}$$

is the matrix representation of the second-order **Christoffel tensor** (generalized for the case of piezoelectric medium).

Bulk acoustic waves in piezoelectric media

Christoffel matrix equation

$$\begin{bmatrix} \mathbb{G} - \rho V^2 \mathbb{1} \end{bmatrix} \mathbb{A}_u = \mathbb{O}, \quad \text{where} \quad \mathbb{G} = \mathbb{N} \mathbb{c} \mathbb{N}^{\mathsf{T}} + \frac{\mathbb{N} \mathbb{e}^{\mathsf{T}} \mathbb{m}^{\mathsf{T}} \mathbb{e} \mathbb{N}^{\mathsf{T}}}{\mathbb{m}^{\mathsf{T}} \mathbb{e} \mathbb{n}}$$

Observations:

- The polarization is eigenvector of the Christoffel tensor (matrix) \mathbb{G} with eigenvalue ρV^2 .
- The phase velocities and polarizations of plane waves propagating in the direction *n* in a crystal are given by the eigenvalues and eigenvectors of the corresponding Christoffel tensor.

Bulk acoustic waves in piezoelectric media

Christoffel matrix equation

$$\begin{bmatrix} \mathbb{G} - \rho V^2 \mathbb{1} \end{bmatrix} \mathbb{A}_u = \mathbb{O}, \quad \text{where} \quad \mathbb{G} = \mathbb{N} \mathbb{C} \mathbb{N}^{\mathsf{T}} + \frac{\mathbb{N} \mathbb{e}^{\mathsf{T}} \mathbb{m}^{\mathsf{T}} \mathbb{e} \mathbb{N}^{\mathsf{T}}}{\mathbb{m}^{\mathsf{T}} \mathbb{e} \mathbb{n}}$$

The **phase velocities** and **polarizations** of plane waves propagating in the direction n in a crystal are given by the **eigenvalues** and **eigenvectors** of the corresponding **Christoffel tensor**.

The acoustic wave propagation in (anisotropic) solids is more complicated that in fluids, because of the following facts.

- Three plane waves with mutually orthogonal polarizations can propagate in the same direction, with different velocities.
- The elastic displacement vector is not generally parallel or perpendicular to the propagation direction. The waves are purely longitudinal or transverse only in particular directions.
- The wave with polarization closest to the propagation direction is called quasi-longitudinal, its velocity is usually higher than that of the two other waves, called quasi-transverse. Only in particular directions are the waves purely longitudinal or transverse.

Characteristic surfaces

- **The velocity surface** is defined by the end of the vector nV(n), drawn from the origin in varied directions n (the length of this vector equals the phase velocity V for waves with wavefronts perpendicular to it).
- **The slowness surface** is defined by the end of vector n/V(n), drawn from the origin in varied directions n. The **energy velocity** is, at all points, **normal to the slowness surface**.
- **The wave surface** is defined by the end of the **energy velocity vector** $V^{e}(n)$, drawn from the origin, as the propagation direction n varies. It is an **equi-phase surface** and describes the points reached, at unit time, by the vibrations (energy) emitted at time zero by a point source at the origin.









Characteristic surfaces (velocity surfaces [km/s] in the YZ-plane),





1 Introduction

2 Piezoelectricity

- The piezoelectric phenomena
- Piezoelectric equations
- Voigt-Kelvin notation

3 Anisotropic media

- Crystalline materials
- Constitutive matrices for some classes of anisotropy

4 Bulk acoustic waves in anisotropic media

- Mathematical description
- Characteristic surfaces

5 Surface Acoustic Waves (SAW)

- Types of Surface Acoustic Waves
- Partial waves
- Rayleigh waves
- Lamb waves
- Decoupling of Rayleigh waves in piezoelectric media

6 SAW examples

- Piezoelectric Rayleigh wave in lithium niobate
- Lamb waves in a lithium niobate plate

Types of Surface Acoustic Waves

- Rayleigh waves waves travelling near the surface of elastic solids
- Lamb waves waves travelling in elastic plates (guided by the surfaces of these plates)
- Love waves horizontally polarized shear waves guided by a thin elastic layer set on another elastic solid (of higher acoustic wave velocity)
- Stoneley waves waves travelling along solid-fluid or solid-solid interfaces

Types of Surface Acoustic Waves

- **Rayleigh waves** waves travelling near the surface of elastic solids
- Lamb waves waves travelling in elastic plates (guided by the surfaces of these plates)
- Love waves horizontally polarized shear waves guided by a thin elastic layer set on another elastic solid (of higher acoustic wave velocity)
- Stoneley waves waves travelling along solid-fluid or solid-solid interfaces

Pseudo-surface waves

A pseudo-surface wave appears in certain crystals when, because of anisotropy, the Rayleigh wave velocity is greater than that of one of the bulk transverse waves.

Anisotropic media

Partial waves (for SAW)

For harmonic wave propagation in the sagittal XZ-plane the waveform is defined as follows:

$$\mathcal{E}(\mathbf{x},t) = \exp[ik(x+\beta z-Vt)], \text{ where } V = \frac{\omega}{k},$$

 ω is the angular frequency, k is the wavenumber, and β is a constant value which defines the direction of propagation in the XZ-plane. Therefore:

$$\mathcal{F}(.) = \exp[ik(.)], \qquad \mathcal{F}'(.) = ik\mathcal{F}(.).$$

Now, when the matrix \mathbb{N} and vector \mathbb{n} are related to the direction of propagation n, they can be specified as follows

$$\mathbb{N} \to \mathbb{B} = \begin{bmatrix} 1 & 0 & 0 & 0 & \beta & 0 \\ 0 & 0 & 0 & \beta & 0 & 1 \\ 0 & 0 & \beta & 0 & 1 & 0 \end{bmatrix}, \qquad \mathbb{n} \to \mathbb{b} = \begin{bmatrix} 1 \\ 0 \\ \beta \end{bmatrix}.$$

Partial waves (for SAW)

For harmonic wave propagation in the sagittal XZ-plane the waveform is defined as follows:

$$\mathcal{E}(\mathbf{x},t) = \exp[ik(x+\beta z-Vt)], \text{ where } V = \frac{\omega}{k},$$

 ω is the angular frequency, k is the wavenumber, and β is a constant value which defines the direction of propagation in the XZ-plane. Therefore, the strain, electric field, stress, and electric displacement vectors are

$$\mathbb{S} = \mathbb{B}^{\mathsf{T}} \mathbb{A}_{\boldsymbol{u}} \mathbf{i} k \mathcal{E}, \qquad \mathbb{E} = -\mathbb{b} A_{\phi} \mathbf{i} k \mathcal{E},$$

$$\mathbb{T} = (\mathbb{c}\mathbb{B}^{\mathsf{T}}\mathbb{A}_{u} + \mathbb{e}^{\mathsf{T}}\mathbb{b}A_{\phi})\mathbf{i}k\mathcal{E}, \qquad \mathbb{D} = (\mathbb{e}\mathbb{B}^{\mathsf{T}}\mathbb{A}_{u} - \mathbb{e}\mathbb{b}A_{\phi})\mathbf{i}k\mathcal{E},$$

and the final set of equations is as follows.

Plane harmonic wave propagation in piezoelectric media

$$\begin{aligned} \left(\mathbb{B} \mathbb{c} \mathbb{B}^{\mathsf{T}} - \rho V^{2} \mathbb{1} \right) \mathbb{A}_{\boldsymbol{u}} + \mathbb{B} \mathbb{e}^{\mathsf{T}} \mathbb{b} A_{\phi} &= 0, \\ \mathbb{b}^{\mathsf{T}} \mathbb{e} \mathbb{B}^{\mathsf{T}} \mathbb{A}_{\boldsymbol{u}} - \mathbb{b}^{\mathsf{T}} \mathbb{e} \mathbb{b} A_{\phi} &= 0. \end{aligned}$$

Partial waves (for SAW)

Plane harmonic wave propagation in piezoelectric media

$$\begin{aligned} (\mathbb{B}\mathbb{c}\mathbb{B}^{\mathsf{T}} - \rho V^{2}\mathbb{1})\mathbb{A}_{u} + \mathbb{B}\mathbb{e}^{\mathsf{T}}\mathbb{b}A_{\phi} &= \mathbb{0}, \\ \mathbb{b}^{\mathsf{T}}\mathbb{e}\mathbb{B}^{\mathsf{T}}\mathbb{A}_{u} - \mathbb{b}^{\mathsf{T}}\mathbb{e}\mathbb{b}A_{\phi} &= 0. \end{aligned}$$

- This plane-wave eigensystem depends now also on β .
- Eigenproblem is solved for β with V treated as parameter. The secular equation is an 8th-order polynomial (or a 6th-order polynomial for purely elastic media).
- The 8 eigenvalues and eigenvectors form 8 **partial waves**. In case of the Rayleigh wave, 4 of them are discarded on the basis of boundary conditions at -∞.
- The solution is a linear combination of partial waves which are coupled by the **boundary conditions** on the surface(s). That gives **another** eigensystem.
- Its secular equation must be zero for the velocity V to be the correct surface wave velocity – this condition is checked and eventually satisfied by an adjusting procedure which changes V in a loop.

Rayleigh waves

A Rayleigh wave propagates along the surface of a medium.



Mechanical boundary conditions:

for
$$z \to -\infty$$
: $u = 0$
for $z = 0$: $T \cdot n = 0$

Electrical boundary conditions:

for
$$z \to -\infty$$
: $\phi = 0$
for $z = 0$: $\boldsymbol{D} \cdot \boldsymbol{n} = 0$

Rayleigh waves

A Rayleigh wave propagates along the surface of a medium.



Features:

- the partial waves are coupled at the surface;
- for a particular material and orientation (the cut and direction of propagation) there is actually only one velocity, i.e., there is only one Rayleigh wave;
- longitudinal and transverse motions decrease exponentially in amplitude as distance from the surface increases (there is a phase difference between these component motions);
- the Rayleigh wave is **non-dispersive**.

Lamb waves

Lamb waves are driven by a plate of finite thickness.



Mechanical boundary conditions:

for
$$z = +h$$
: $T \cdot n = 0$
for $z = -h$: $T \cdot n = 0$

Electrical boundary conditions:

for
$$z = +h$$
: $\boldsymbol{D} \cdot \boldsymbol{n} = 0$
for $z = -h$: $\boldsymbol{D} \cdot \boldsymbol{n} = 0$

Lamb waves

Lamb waves are driven by a plate of finite thickness.



Features:

- partial waves are coupled and also reflected back and fourth by the boundaries of the plate;
- coupled waves results from the travelling waves along the plate and standing waves in the direction across the plate thickness;
- there are many modes (symmetric and antisymmetric) with different velocities;
- dispersion (the wave velocities depend on the frequency and the plate thickness).

Piezoelectricity Anisotropic media

Decoupling of Rayleigh-type piezoelectric waves

- When the sagittal plane is normal to a direct binary axis of crystal, there exists the possibility for:
 - a non-piezoelectric Rayleigh wave R₂ polarized in this plane $(u_2 = 0),$
 - a piezoelectric transverse horizontal wave TH (BLEUSTEIN & GULYAEV, 1968) which can propagate independently.
- 2 When the sagittal plane is parallel to a mirror plane of crystal, there exists the possibility for:
 - a piezoelectric Rayleigh wave \overline{R}_2 polarized in the sagittal plane $(u_2 = 0),$
 - a non-piezoelectric transverse horizontal wave TH which can propagate independently and is not a surface wave.

Decoupling of Rayleigh-type piezoelectric waves

- When the sagittal plane is normal to a direct binary axis of crystal, there exists the possibility for:
 - a non-piezoelectric Rayleigh wave R₂ polarized in this plane $(u_2 = 0),$
 - a piezoelectric transverse horizontal wave TH (BLEUSTEIN & GULYAEV, 1968) which can propagate independently.
- 2 When the sagittal plane is parallel to a mirror plane of crystal. there exists the possibility for:
 - a piezoelectric Rayleigh wave \overline{R}_2 polarized in the sagittal plane $(u_2 = 0),$
 - a non-piezoelectric transverse horizontal wave TH which can propagate independently and is not a surface wave.
- The symmetries of these two cases can be satisfied only for orthorhombic, tetragonal, hexagonal, and cubic crystals. With respect to the crystallographic axes there are **16 possible combinations**, that is, orientations of the propagation direction x_1 and the sagittal plane normal x_2 .
- Decoupling is also possible in trigonal crystals: for the so-called Y-cut (i.e., the free surface is parallel to the XZ-plane) when the propagation is along the Z-axis (the sagittal plane is YZ).

Decoupling of Rayleigh-type piezoelectric waves

Trigonal system – class 3m – rotated around X-axis



- zero component
- : non-zero component

(interdependencies are not shown)

1 Introduction

2 Piezoelectricity

- The piezoelectric phenomena
- Piezoelectric equations
- Voigt-Kelvin notation

3 Anisotropic media

- Crystalline materials
- Constitutive matrices for some classes of anisotropy

4 Bulk acoustic waves in anisotropic media

- Mathematical description
- Characteristic surfaces

5 Surface Acoustic Waves (SAW)

- Types of Surface Acoustic Waves
- Partial waves
- Rayleigh waves
- Lamb waves
- Decoupling of Rayleigh waves in piezoelectric media

6 SAW examples

- Piezoelectric Rayleigh wave in lithium niobate
- Lamb waves in a lithium niobate plate

Example 1: Rayleigh wave

Rayleigh wave \overline{R}_2 (Litium niobate, Y-cut, propagation-Z, velocity: 3485 m/s)



Electric potential of the associated electric field (phase angle: 0°)

Wave velocities (LiNbO₃ Y-cut, propagation direction Z)



Antisymmetric modes (LiNbO₃ Y-cut, propagation direction Z)

1st antisymmetric mode (sagittal plane)

another antisymmetric mode (sagittal plane)

Symmetric mode (LiNbO₃ Y-cut, propagation direction Z)

sagittal plane

the wave polarization is in the sagittal plane

free surface

Symmetric mode (LiNbO₃ Y+128°-cut, propagation direction X)

sagittal plane

the wave polarization is OUT of the sagittal plane

free surface